


Specifications

Nominal Voltage		12V
Rated Capacity(20 hour rate)		26Ah
Dimensions	Total Height (with terminals)	6.85inches(174mm)
	Height	6.85inches(174mm)
	Length	6.54inches(166mm)
	Width	4.96inches(126mm)
Weight		Approx. 18.48pound(8.4kg)


Discharge Curves 77 °F(25 °C)



Characteristics

Capacity 77 °F(25 °C)	20 hour rate (1.30A)	26.0Ah
	10 hour rate (2.41A)	24.1Ah
	5 hour rate (4.16A)	20.8Ah
	1 hour rate (15.6A)	15.6Ah
	15 minute Rate (45.72A)	11.43Ah
Internal Resistance	Full charged Battery 77°F(25°C)	10mΩ
Capacity affected by Temperature (20 hour rate)	104°F(40°C)	102%
	77°F(25°C)	100%
	32°F(0°C)	85%
	5°F(-15°C)	65%
Self-Discharge 77°F(20°C)	Capacity after 3 month storage	91%
	Capacity after 6 month storage	81%
	Capacity after 2 month storage	60%
Max. Discharge Current 77°F(25°C)	390A(5S)	
Terminal	M4	
Charge (Constant Voltage)	Cycle	Initial Charging Current less than 7.8A Voltage 14.4~14.7V/77 F(25 C)
	Float	Voltage 13.5~13.8V/77 F(25 C)

Relationship between charge voltage and temperature



Constant Current Discharge

(AMPERES @25°C)

F.V/Time	5Min	10Min	15Min	30Min	60Min	2H	3H	4H	5H	10H	20H
9.60	99.06	62.92	50.44	28.08	17.16	9.70	6.68	5.36	4.52	2.47	1.32
9.90	96.72	61.10	48.62	27.30	16.72	9.36	6.60	5.30	4.51	2.45	1.31
10.20	92.30	58.50	47.06	26.78	16.25	9.23	6.53	5.25	4.47	2.43	1.31
10.50	88.40	56.16	45.24	26.52	15.86	9.10	6.50	5.20	4.42	2.43	1.30
10.80	83.20	55.64	42.90	25.74	15.34	8.84	6.40	5.07	4.37	2.37	1.28


Constant Power Discharge

(WATTS PER CELL@25°C)


F.V/Time	5Min	10Min	15Min	30Min	60Min	2H	3H	4H	5H	10H	20H
9.60	1103.53	707.22	573.00	320.11	198.03	113.35	79.45	63.79	53.93	29.54	15.82
9.90	1078.43	687.38	552.81	312.59	193.26	109.49	78.65	63.28	53.81	29.32	15.76
10.20	1030.07	658.71	535.54	306.90	188.01	108.18	77.82	62.71	53.43	29.09	15.71
10.50	987.43	633.48	515.28	304.18	183.66	106.83	77.55	62.14	52.86	29.10	15.65
10.80	930.18	628.73	489.12	295.50	177.94	103.87	76.43	60.64	52.30	28.45	15.39

The operating environment temperature above 40°C should be avoided. After long term storage, The battery actual capacity would be less than the rated capacity. Full capacity will be obtained through several charge/discharge cycles. To get the longest life, KSTAR battery should be fully charged before storage.


Cycle service life in relation to depth of discharge




Constant voltage charge characteristic




Self-Discharge Characteristics.



Relationship of OCV and Residual Capacity % (25 °C)



Temperature effects on capacity



Temperature effects on float life

